



1 L | 1211146-001 4 L | 1211146-004 10 L | 1211146-010 20 L | 1211146-020 20 L | 1211146-B20 60 L | 1211146-D60 208 L | 1211146-D68 208 L | 1211146-D28

# **RAVENOL ATF T-ULV FLUID**

**Category** Gear oil for automatic transmissions **Item number** 1211146

**Oil type** Synthetic

**Recommendation** ATF AW-2, BMW 83 22 2 413 477 (8-Speed AT BMW GA8G45AW), BMW ATF 7, PSA 16 350 560 80 (8-Speed AT PSA AMN8/ATN8/AXN8), VOLVO 31492172 (8-Speed AT AWF8G45), VOLVO 31492173 (8-Speed AT AWF8G55), VW G 053 001 A2 (8-Speed AT VW 09S (AQ300-8F))

#### New products 1

**RAVENOL ATF T-ULV Fluid** is a fully synthetic ATF (Automatic Transmission Fluid), designed on the basis of high quality polyalphaolefin (PAO) and Esters with a special additive and inhibition, which ensure a perfect function of the automatic transmission.

**RAVENOL ATF T-ULV Fluid** is an ATF for the latest generation of Aisin Warner automatic transmissions. It guarantees a high wear protection in all operating conditions. **RAVENOL ATF T-ULV Fluid** has a red colour.

Reducing loss torque in automatic transmissions (ATFs) is a key factor in improving fuel economy. A promising approach is to reduce the viscosity of the Automatic Transmission Fluid (ATF) to minimize churning loss. RAVENOL has developed an ultra-low viscosity ATF, called "T-ULV", which has approximately 50% lower kinematic viscosity at 40 °C compared to the conventional low viscosity ATFs. It is generally understood that if the viscosity of an ATF is too low, it can have a negative impact on the fatigue life of components such as gears and bearings, and possibly lead to increased wear or seizure. RAVENOL ATF T-ULV Fluid was designed to solve these problems via the application of two key technologies. The first is a high performance PAO (Polyalphaolefin) with a low traction coefficient, which translates to low viscosity under high pressure conditions. This decreases the shear resistance between sliding surfaces under elasto-hydrodynamic lubrication (EHL) conditions, which contributes to improving the fatigue life of bearings and other components. The second is an ester type base oil with high polarity. It was found that the amount of ester base oil used has a major influence on fatigue life. The adsorption of esters onto metal surfaces is thought to improve lubricity in severe lubrication conditions. Durability tests were performed in a wide range of conditions, using gear and bearing components and actual transmission units, and it was confirmed that

**RAVENOL ATF T-ULV Fluid** outperforms low viscosity ATFs, despite its ultra-low viscosity. Furthermore, **RAVENOL ATF T-ULV Fluid** reduces loss torque in the transmission by approximately 12% compared to other low viscosity ATFs.

### **Application Note**

**RAVENOL ATF T-ULV Fluid** is an Ultra Low Viscosity ATF for modern 8-Speed automatic transmissions of Aisin Warner.

**RAVENOL ATF T-ULV Fluid** is suitable for use in automatic transmissions of BMW, Peugeot/Citroen, VW, Volvo. Note the original part number of manufacturer!

#### **Characteristics**

- Very good lubricity also at low temperatures in winter
- High, stable viscosity index
- Very good oxidation stability
- Excellent wear, corrosion and foaming protection
- Excellent friction constant
- High thermal and oxidative stability
- Excellent cooling capacity

## **Technical Product Data**

Density at 20 °C	819,3		EN ISO 12185
Colour	Rot		VISUELL
Viscosity at 100 °C	3,3	mm²/s	DIN 51562-1
Viscosity at 40 °C	12,0	mm²/s	DIN 51562-1
Viscosity Index VI	151		DIN ISO 2909
Brookfield Viscosity at -40 °C	1090	mPa*s	ASTM D2983
Pourpoint	-78	°Celsius	DIN ISO 3016
Seq. I at 24 °C	10/0		ASTM D892
Seq. II at 93,5 °C	0/0		ASTM D892
Seq. II at 93,5 °C Seq. III at 24 °C after 93,5 °C	0/0 10/0		ASTM D892 ASTM D892
		N	
Seq. III at 24 °C after 93,5 °C	10/0	N mm²/s	ASTM D892
Seq. III at 24 °C after 93,5 °C VKA Four Ball Test (Wear)	10/0 0,6		ASTM D892 DIN 51350-3
Seq. III at 24 °C after 93,5 °C VKA Four Ball Test (Wear) VKA Four Ball Test (EP Extreme Pressure)	10/0 0,6 <2000	mm²/s	ASTM D892 DIN 51350-3 DIN 51350-3
Seq. III at 24 °C after 93,5 °C   VKA Four Ball Test (Wear)   VKA Four Ball Test (EP Extreme Pressure)   Brookfield Viscosity at -50 °C	10/0 0,6 <2000 5800	mm²/s mPa*s	ASTM D892 DIN 51350-3 DIN 51350-3 ASTM D2983

09.12.2021